

**REMARKS/ARGUMENTS**

This Reply is in response to the Office Action dated January 11, 2006 and is accompanied by a petition for a one-month extension of time along with an authorization to charge the required statutory fee for the extension.

In this Reply, claims 1-4, 26 and 32 have been amended and claims 31 and 36 have been cancelled. Claims 72-74 have been added. Support for the recited pH of 1 recited in claim 72 can be found in Example 6 which recites a pH range of 1 to 13, while support for a pH of 6 can be found in the summary as well as in original claim 33. New independent claim 73 recites "A slurry for chemical mechanical polishing (CMP), comprising: a bulk solution, said bulk solution being in a pH range of 1 to 6 or 8 to 13, and a plurality of nanoporous comprising particles". Support for the recited pH ranges can be found in Applicants' summary. No new matter has been added.

In Applicants' Reply filed on October 27, 2005, claim 1 was amended to recite a slurry comprising "a plurality of *nanoporous* comprising particles" to distinguish U.S. 6,048,577 to Garg who discloses a polishing slurry including only nanosize (but not nanoporous) particles. However, in the instant action, although the anticipation rejections based on Garg and obviousness rejections based on Garg in view of U.S. 6,458,017 to Li were withdrawn, the Examiner identified a new reference to formulate new obviousness rejections.

Specifically, claims are rejected based on newly cited U.S. Pat. 5,055,019 to Meyer et al. (cited for nanoporous particles) combined with Garg. According to the Examiner:

Garg teaches nano-sized powder of alpha alumina having silica coating thereon (column 5, lines 7-10). Garg further teaches a polishing slurry is comprised of a alumina powder has a silica coating wherein 95% of the particles have widths of from 20 to about 50 nanometers while less than 5% have particle sizes greater than 100 nanometers and is dispersed in a liquid dispersion medium (claims 6 and 9). The aforementioned reads on,

**A slurry for chemical mechanical polishing (CMP), comprising:  
a bulk solution; and**

**a plurality of particles, in claim 1; and**

**encompasses an average particle size of said nanosize comprising particles is less than 500 nm, in claim 9 and is from 200 to 500 nm, in claim 10.**

Garg differs if failing to teach a plurality of nanoporous comprising particles, in claims 1, 5, 6, and 9.

Meyer discloses boehmitic alumina compounds having  $\text{Al}_2\text{O}_3$  and the compounds have a pore radii in the range of 3 to 100 nm (Abstract and column 1, lines 6-10), which reads on a plurality of nanoporous comprising particles.

Since Meyer illustrates a plurality of nanoporous comprises particles is known, then it would have been obvious to one having ordinary skill in the art at the time the invention was made to modify Garg's slurry by employing compounds having a pore radii in the nm range as taught by Meyer, including applicants' specifically claimed range because such compounds can be used in polishing agents (Meyer, column 1, lines 11-16).

Applicants respectfully disagree with the assertion of obviousness based on Garg in view of Meyer. However, before reviewing the cited art, Applicants will review the claimed invention as now recited in amended claim 1 (copied below).

1. (Currently amended) A slurry for chemical mechanical polishing (CMP), comprising:  
a bulk solution including at least one additive selected from the group consisting of  
an oxidizer, a selective adsorption additive and a salt, and;  
a plurality of nanoporous comprising particles.

The amendment to claim 1 thus adds an "additive selected from the group consisting of an oxidizer, a selective adsorption additive and a salt". Such additives are specific to chemical mechanical polishing (CMP), which is the basis of Applicants' claimed invention. Unlike CMP which relies on mechanical action as well as chemical action, general mechanical polishing, even when slurries are used, rely entirely on mechanical abrasion and thus do not include any of the recited additives recited in amended claim 1. For example, the oxidizer recited in claim 1 is clearly specific for the CMP of metals.

Applicants have included text which distinguishes CMP processing from both mechanical polishing (disclosed by Garg and Meyer) and chemical etching. This article was published in MRS Bulletin October 2002 (full copy attached; salient details copied below):

The CMP process is often confused with chemical etching, and/or mechanical polishing process. All the three processes achieve controlled material removal; however the mechanisms by which material removal is achieved are completely different. In a chemical etching process, material removal is achieved by a chemical reaction at the surface, resulting in the formation of dissolved species and subsequent transportation of the dissolved species from the surface. The etching rate/removal rate is constant and does not change with time. This is shown schematically in Fig. 3. In the CMP process, the chemical reactions between the chemicals and the metallic layers result in a thin, non-dissolving and chemically passivating surface film which is subsequently removed by the mechanical action of the particles. Initially the chemical reaction rate is high, but due to passivation effects, the reaction rate drops immediately. When the surface layer is removed by abrasive particles in the slurry, the surface film formation and passivation

phenomenon repeats itself (Fig. 3). Thus, static etch rate in a CMP process is quite low. In dielectric CMP, although surface passivation is not a critical issue, the formation of a soft hydrated gel-like layer on the surface is important to achieve high performance polishing.

In mechanical polishing, the removal of material takes place by direct interaction of particles on the original surface. The material removal in this case can be considered to be due to the classical abrasion wear mechanism which involves indentation and the removal of material by a scratching process. This material removal mechanism typically requires high energy because bonds have to be broken by mechanical forces only. Due to large energy requirements, the removal rates are typically much lower than CMP unless larger sized particles are used, in which case high surface defectivity is obtained. Thus, an inverse relationship typically exists between the rate of removal and the surface finish. In contrast, in a CMP process, the chemical modified surface layer is much easily removed because of its inherent nature: soft, ductile layer in the case of silica and more brittle layers in the case of metals such as tungsten, copper, etc. Figure 5 shows schematically the relationship between removal rate and surface finish for all three material removal processes.

Garg is entitled "Nano-sized alpha alumina particles having a silica coating thereon" and discloses nano-sized powders of alpha alumina can be obtained from a boehmite gel doped with a barrier-forming material such as silica that is then dried, fired and comminuted to powder form. The only mention of porosity in Garg regarding porosity is in the background regarding "porous nature of the boehmite particles" as copied below:

One of the problems in working with a boehmite gel to produce formed ceramic articles is that the gel cannot exceed about 65 wt % solids because of the *porous* nature of the boehmite particles. Thus there is a lot of water that needs to be driven off in the course of the drying process. In addition not only is there further shrinkage as a result of the elimination of the water associated with the boehmite, (which is of course alpha alumina monohydrate), but the phase change from the intermediate gamma phase (to which the boehmite first converts) to the final alpha phase also involves a shrinkage. Thus the direct fabrication of a ceramic product from boehmite is only practical for thin objects where the water loss can be relatively easily be accommodated and the shrinkages can be controlled.

In one embodiment, Garg's does disclose a polishing slurry comprising a powder dispersed in a liquid dispersion medium (claims 9 and 10). However, Garg does not mention CMP and does not disclose or suggest Applicants' claimed CMP slurry including the claimed "nanoporous comprising particles" or the newly recited "additive selected from the group consisting of an oxidizer, a selective adsorption additive and a salt".

Meyer is entitled "Process for the production of boehmitic aluminas" and discloses a process for the preparation of boehmitic alumina compounds having a purity of, at least, 99.95%  $\text{Al}_2\text{O}_3$ . The compounds produced according to the invention have a pore radii in the range of 3 to 100 nm. The preparation of such compounds is carried out by, first, obtaining an alumina suspension from a neutral aluminum alkoxide hydrolysis and, then, aging the alumina suspension in an autoclave, preferably, at a steam pressure of 1 to 30 bar, corresponding to a temperature of 100 degree C. to 235 degree C., for between 0.5 and 20 hours. The aging step of the invention is preferably carried out with stirring at a peripheral speed of 1 to 6 m/s.

As noted above, to base an obviousness rejection of former claim 1 the Examiner combined Garg and Meyer based on the following reasoning:

Since Meyer illustrates a plurality of nanoporous comprises particles is known, then it would have been obvious to one having ordinary skill in the art at the time the invention was made to modify Garg's slurry by employing compounds having a pore radii in the nm range as taught by Meyer, including applicants' specifically claimed range because such compounds can be used in polishing agents (Meyer, column 1, lines 11-16).

Applicants acknowledge that Meyer mentions in a single place (cited by the Examiner) that the nanoporous particles according to Meyer can be used for "polishing". Applicants have copied the full paragraph below relied on by the Examiner.

In the neutral hydrolysis of aluminum alkoxides, e.g., as described in DE-AS 1 258 854, aluminas with a boehmite structure or  $\alpha$ -aluminum oxide monohydrate are obtained. The products obtained have a maximum pore radius of 2 to 4 nm and can be used as pigments, fillers, polishing agents and catalyst carriers. *However, it is particularly desirable, in the case of carrier materials for catalysts and for separating gaseous components, that such aluminas are obtained with a pore volume or with pore radii in a specific range. It is particularly desirable to increase*

*the pore volume of such aluminas and also to increase the pore radius, while maintaining a very narrow pore radius distribution.*

Significantly, Meyer discloses the invention is "particularly desirable, in the case of carrier materials for catalysts and for separating gaseous components". Applicants note that in the case of catalysis, more surface area is clearly desirable as it increases surface area for the reaction to take place. In contrast, there is no apparent advantage in using porous particles for polishing (as compared to conventional solid particles). Significantly, particle porosity is well known by those having ordinary skill in the art to reduce the mechanical integrity of the particles. For example, one having ordinary skill in the art of mechanical polishing porosity would readily appreciate that porosity of any kind would mechanically weaken the particles and make the particles susceptible to fracture or even pulverization during mechanical polishing. Thus, since mechanical integrity is a known problem regarding porous particles and no advantages regarding porous particles are disclosed or known to those having ordinary skill in the art, porous particles including nanoporous particles are taught away from for mechanical polishing applications.

Moreover, Applicants can find no suggestion or motivation to modify Garg to add the nanoporosity disclosed in Meyer in any of the references of record in this case. MPEP 2143.01 entitled "Suggestion or Motivation to Modify the References" describes the required elements necessary under the Patent Law to properly support a finding of a motivation to modify references. A portion thereof is copied below:

In determining the propriety of the Patent Office case for obviousness in the first instance, it is necessary to ascertain whether or not the reference teachings would appear to be sufficient for one of ordinary skill in the relevant art having the reference before him to make the proposed substitution, combination, or other modification." In re Linter, 458 F.2d 1013, 1016, 173 USPQ 560, 562 (CCPA 1972).

*Obviousness can only be established by combining or modifying the teachings of the prior art to produce the claimed invention where there is some teaching, suggestion, or motivation to do so found either explicitly or implicitly in the references themselves or in the knowledge generally available to one of ordinary skill in the art.* "The test for an implicit showing is what the combined teachings, knowledge of one of ordinary skill in the art, and the nature of the problem to be solved as a whole would have suggested to those of ordinary skill in the art." In re Kotzab, 217 F.3d 1365, 1370, 55 USPQ2d 1313, 1317 (Fed. Cir. 2000). See also In re Fine, 837 F.2d 1071, 5 USPQ2d 1596 (Fed. Cir. 1988); In re Jones, 958 F.2d 347, 21 USPQ2d 1941 (Fed. Cir. 1992).

Regarding Applicants' recited nanoporosity, the Examiner asserts that the motivation to add the nanoporosity disclosed in Meyer to Garg's slurry is "because such compounds can be used in polishing agents".

Applicants respectfully traverse the above-provided motivation to add the recited nanoporosity to Garg's slurry particles. The single mention in Meyer that nanoporous particles can be used in polishing, without the recognition of any advantages thereof, does not provide the required "teaching, suggestion, or motivation" to modify be "found either explicitly or implicitly in the references themselves or in the knowledge generally available to one of ordinary skill in the art. Without the benefit of Applicants' application one having ordinary skill in the art would not specifically recognize the advantages of the recited nanoporosity for CMP described in Applicants' application which have unexpected found to provide improved CMP results. As noted above, nanoporosity is taught away since one having ordinary skill in the art of mechanical polishing would recognize that porosity of any kind would mechanically weaken the particles and make them susceptible to fracture or even pulverization. Accordingly, absent impermissible hindsight regarding Applicants' findings, one having ordinary skill in the art would not recognize a single advantage of nanoporosity for CMP particles as described by Applicants. Accordingly, since there is no motivation for one having ordinary skill in the art to modify Garg's slurry particles to add nanoporosity, and the mechanically compromised porous particles would

themselves teach away from use for polishing, amended claim 1 is believed to recite an inventive step and thus render claim 1 and claims dependent thereon patentable over the cited art.

In addition, following Applicants' amendment to claim 1, Applicants note that Garg and Meyer are now both clearly unrelated art relative to Applicants' claimed CMP slurry which now recites a CMP specific additive. Although Garg discloses a polishing slurry, the slurry is a simple mechanical polishing slurry. Meyer's single mention of the nanoporous particles for "polishing" does not mention a polishing slurry, nor clearly CMP. Accordingly, both Garg and Meyer are wholly unrelated to CMP. As noted above, while general mechanical polishing, even when slurries are used, rely entirely on mechanical abrasion, CMP relies on mechanical action as well as chemical action, and thus requires chemically active additive(s) to achieve the desired action. Applicants have copied MPEP 2141.01(a) below to emphasize that *at least Meyer is nonanalogous art.*

#### **2141.01(a) Analogous and Nonanalogous Art**

**TO RELY ON A REFERENCE UNDER 35 U.S.C. 103, IT MUST BE ANALOGOUS PRIOR ART**

The Examiner must determine what is "analogous prior art" for the purpose of analyzing the obviousness of the subject matter at issue. "In order to rely on a reference as a basis for rejection of an applicant's invention, the reference must either be in the field of applicant's endeavor or, if not, then be reasonably pertinent to the particular problem with which the inventor was concerned." *In re Oetiker*, 977 F.2d 1443, 1446, 24 USPQ2d 1443, 1445 (Fed. Cir. 1992). See also *In re Deminski*, 796 F.2d 436, 230 USPQ 313 (Fed. Cir. 1986); *In re Clay*, 966 F.2d 656, 659, 23 USPQ2d 1058, 1060-61 (Fed. Cir. 1992) ("A reference is reasonably pertinent if, even though it may be in a different field from that of the inventor's endeavor, it is one which, because of the matter with which it deals, logically would have commended itself to an inventor's attention in considering his problem."); and *Wang Laboratories Inc. v. Toshiba Corp.*, 993 F.2d 858, 26 USPQ2d 1767 (Fed. Cir. 1993).

Applying the above rule, Meyer is clearly outside Garg's field of endeavor, that being polishing slurries. Meyer is also not reasonably pertinent to the problem at hand, mechanically



polishing a surface using a slurry, as Meyer does not relate to slurries for polishing at all. Accordingly, Applicants submit that one having ordinary skill in the art reading Garg would not consider Meyer's nanoporous particles since Meyer is nonanalogous art to slurry-base polishing.

Some claims are believed to provide separate bases for patentability. For example, amended claim 2 recites "The slurry of claim 1, wherein said additive comprises said selective adsorption additive", such as a surfactant or surface active polymer. As taught in the present application, the claimed nanoporous slurry particles provide unexpected and highly advantageous results, particularly when used in conjunction with Applicants' selective adsorption additive comprising slurry recited in claim 2. Specifically, in this arrangement, because of the porous particle surface, the adsorption of surfactants or polymer additives can occur at different, and generally lower, concentrations as compared to bulk particles.

Moreover, claim 6 which recites "wherein said nanosize nanoporous particles comprise nanoporous cores coated with a solid material coating or first core material coated with a second material, said second material being a nanoporous coating" appears to have been improperly rejected because no basis in the cited art for the limitation recited is provided.

New independent claim 73 recites "A slurry for chemical mechanical polishing (CMP), comprising: a bulk solution, said bulk solution being in a pH range of 1 to 6 or 8 to 13, and a plurality of nanoporous comprising particles". The pH, like Applicants slurry additives recited in amended claim 1 are specific to CMP. In contrast, mechanical polishing slurries are essentially neutral (pH of 7). Accordingly, for reasons analogous to those described above relative to amended claim 1, claim 73 and its dependent claim are believed to recite an inventive step and thus be patentable over the cited art.

Conclusion

Accordingly, in view of the above, Applicants submit amended claim 1 which recites a slurry for chemical mechanical polishing (CMP), comprising a plurality of nanoporous comprising particles together with a bulk solution including at least one (CMP SPECIFIC) "additive selected from the group consisting of an oxidizer, a selective adsorption additive and a salt" is patentable over the cited art, as are claims dependent thereon. Similarly, new claim 73 which recites a slurry for chemical mechanical polishing (CMP), comprising a plurality of nanoporous comprising particles together with a bulk solution being in a (CMP SPECIFIC) pH range of 1 to 6 or 8 to 13 is patentable over the cited art, as is its dependent claim. Applicants have made every effort to present claims which distinguish over the cited art, and it is believed that all claims are now in condition for allowance. However, Applicants request that the Examiner call the undersigned if anything further is required by the Examiner prior to issuance of a Notice of Allowance for all claims.

Respectfully submitted,

Date: May 11, 2006

Neil R. Jetter, Reg. No. 46,803  
AKERMAN SENTERFITT  
222 Lakeview Avenue; Suite 400  
P.O. Box 3188  
West Palm Beach, FL 33402-3188  
(561) 653-5000

Docket No. 5853-224

# Advances in Chemical-Mechanical Planarization

Rajiv K. Singh and Rajeev Bajaj,  
Guest Editors

## Abstract

The primary aim of this issue of *MRS Bulletin* is to present an overview of the materials issues in chemical-mechanical planarization (CMP), also known as chemical-mechanical polishing, a process that is used in the semiconductor industry to isolate and connect individual transistors on a chip. The CMP process has been the fastest-growing semiconductor operation in the last decade, and its future growth is being fueled by the introduction of copper-based interconnects in advanced microprocessors and other devices. Articles in this issue range from providing a fundamental understanding of the CMP process to the latest advancements in the field. Topics covered in these articles include an overview of CMP, fundamental principles of slurry design, understanding wafer-pad-slurry interactions, process integration issues, the formulation of abrasive-free slurries for copper polishing, understanding surface topography issues in shallow trench isolation, and emerging applications.

**Keywords:** chemical-mechanical planarization, chemical-mechanical polishing, CMP, copper interconnects, low-k dielectrics, nanolithography, shallow trench isolation, silica polishing, slurry design

## Introduction

In the past decade, chemical-mechanical planarization (CMP), also known as chemical-mechanical polishing, has emerged as the fastest-growing operation in the semiconductor manufacturing industry, and it is expected to show equally explosive growth in the future.<sup>1</sup> It is estimated that more than 150 million planarization operations will be conducted this year, and that number is expected to double within the next three years.<sup>2</sup> This rapid increase will be fueled by the introduction of copper-based interconnects for logic and other devices.<sup>3</sup> Other novel applications of CMP for next-generation nanoscale devices are rapidly emerging.

The market size for CMP equipment and consumables (slurries, pads, etc.) grew from \$250 million in 1996 to over \$1 billion in 2000.<sup>4</sup> The consumables market, especially in the area of slurries, is quite robust and is expected to increase from the

present level of \$250 million to more than \$800 million within the next five years.<sup>3</sup> The slurries, which typically contain particle-based abrasives and chemical additives, represent the largest value-added application of nanoparticles—a key area of nanotechnology that is currently garnering substantial funding from governmental organizations and private corporations. It has been estimated that CMP nanoparticles alone will constitute nearly 60% of the total \$1 billion worldwide market for nanopowders by 2005.

One of the unique aspects of CMP is that the process was invented, developed, and put into application by the industry itself without any significant interaction with academic institutions. Consequently, the whole process is shrouded in secrecy, with most of the literature available in the form of patents. The composition of the slurry is the most secretive element. A casu-

ality of this approach has been the lack of a fundamental understanding of the CMP process. This lack is further compounded by the large number of input variables (>20) and output variables (>4) that need to be optimized.<sup>5</sup> Furthermore, the science of CMP is quite different from traditional semiconductor manufacturing technology, which is based on film deposition, ion implantation, photolithography, thermal annealing, vapor-phase processing, and so on.<sup>6</sup> For CMP, an entirely new knowledge base and set of skills, involving particle technology, corrosion, tribology and tribochemical phenomena, wet and surface chemistry, fluid flow, and mechanical properties of polymers, are considered essential.<sup>5</sup> These areas traditionally have not been the focus of semiconductor manufacturing practitioners.

All of these factors have contributed to the impression that CMP is more of an art than a science. Furthermore, misconceptions exist among semiconductor manufacturing practitioners because of a failure to distinguish CMP from other controlled material-removal techniques such as chemical etching and mechanical polishing. As an example, the most widely used fundamental equation in CMP, Preston's law, is nonetheless flawed, as it is solely based on concepts derived from mechanical polishing.<sup>7-9</sup> Further insights into this aspect are discussed in the next section.

The articles in this issue not only provide glimpses into technological advances in the CMP process, but also give a solid framework for understanding CMP phenomena. Important materials-related issues are highlighted. This overview provides a brief description of the process, some key advancements, and emerging applications of CMP.

## Brief Description of the Process

CMP combines chemical and mechanical interactions to planarize metal and dielectric surfaces using a slurry composed of chemicals and submicron-sized particles.<sup>3</sup> A schematic diagram of the CMP operation is shown in Figure 1. The slurry is fed onto a polishing pad made of a porous polymer. By moving the pad across the wafer in a circular, elliptical, or linear motion, the wafer surface is polished. The polymeric pad performs several functions, including uniform slurry transport, distribution and removal of the reacted products, and uniform distribution of applied pressure across the wafer. In a typical CMP process, the chemicals interact with the material to form a chemically modified surface. Simultaneously, the abrasives in the slurry mechanically interact with the chemically modified surface layers, resulting in material removal.<sup>10</sup>

## Advances in Chemical-Mechanical Planarization




Figure 1 Schematic diagram of a typical chemical-mechanical planarization (CMP) process.  $\omega_c$  and  $\omega_p$  refer to the angular velocity of the carrier and the platen, respectively

A mechanistic understanding of the CMP process can be developed by studying the wafer-pad-slurry interactions that occur at both the micro- and nanoscale (Figure 2).<sup>11,12</sup> At the microscale, the rough pad carrying the particle-based slurry interacts with the surface of the wafer. It is generally believed that the particles, which are between the wafer and the pad, participate in a mechanical abrasion process that results in material removal. At the nanoscale, the kinetics of the formation and removal of the thin surface layer controls CMP output parameters such as removal rate, surface planarity, surface defectivity, and slurry selectivity (the polishing rate of the top layer as compared with the underlying layer).




Figure 2 Schematic diagram depicting (a) microscale and (b) nanoscale phenomena that occur during CMP.

Although the CMP process is intuitively quite simple, achieving a more detailed understanding has been limited primarily by the large number of input variables in the polishing process. Table I lists the various systems-level variables in CMP. They include slurry variables (such as particles and chemicals), pad variables, tool variables (down pressure and linear velocity), and substrate variables (pattern density, etc.).<sup>5</sup> The total number of variables can exceed 20, making the process difficult to understand and control. Time-dependent contributions by some of these variables cause further complexities in the process.

As mentioned earlier, the CMP process is often confused with chemical etching or mechanical polishing. All three processes achieve controlled material removal; however, the mechanisms by which material removal is achieved are completely different. In a chemical-etching process, material removal is achieved by a chemical reaction at the surface, resulting in the formation of dissolved species and subsequent transportation of the dissolved species from the surface. The etching (removal) rate is constant and does not change with time. This is shown schematically in Figure 3. In the CMP process, the reactions between the chemicals and the metallic layers result in a thin, nondissolving, chemically passivating surface film that is subsequently removed by the mechanical action of the particles. Initially, the chemical reaction rate is high, but due to passivation effects, the reaction rate drops

immediately. When the surface layer is removed by the abrasive particles in the slurry, the surface-film formation and passivation phenomenon repeats itself (Figure 3). Thus, the static etch rate in CMP is quite low. In CMP of dielectric materials, although surface passivation is not a critical issue, the formation of a soft, hydrated gel-like layer on the surface is important in order to achieve high-performance polishing.

The CMP phenomena can be simulated by tribochemical experiments that involve sliding a ball across the surface of a sample.<sup>13</sup> Figure 4 shows the results obtained from abrading a tungsten substrate subjected to various chemical and electrochemical conditions with an alumina ball. The transient electrochemical current was measured during the oscillating sliding motion of the ball. The current density indicates the formation of the reacted layer on the surface. The figure shows that the layer formation rate (current density) is very high when the ball slides across the tungsten plate and decreases significantly when the tribological motion is stopped.

The CMP phenomena, especially in metals, are very similar to the results of these experiments. Slurry chemicals and particles are chosen appropriately to modulate this interaction process. The article by Singh et al. in this issue provides details on the mechanism of CMP as well as the principles behind slurry design—one of the most important and perhaps least understood aspects of the CMP process.

In mechanical polishing, the removal of material results from the direct interaction of particles on the original surface, that is, the classical abrasion-wear mechanism, which involves indentation of the surface and the removal of material by a scratching process.<sup>14</sup> This material-removal mechanism typically requires high energy because bonds have to be broken using only mechanical forces. Due to the large energy requirements, removal rates are typically much lower than CMP unless larger-sized particles are used, in which case high surface defectivity results. Thus, an inverse relationship typically exists between the rate of removal and the fineness of the surface finish. In contrast, in a CMP process, the chemically modified surface layer is much more easily removed because of its inherent nature: a soft, ductile layer in the case of silica and more brittle layers in the case of metals such as tungsten and copper. Figure 5 shows the relationship between removal rate and surface finish for all three material-removal processes.

Currently, the most widely used equation in CMP is Preston's law, which states that the removal rate of a material is directly proportional to the applied pressure

## Advances in Chemical-Mechanical Planarization


**Table 1: Correlation of Systems-Level Variables with Micro- and Nanoscale Effects and Output Parameters in Chemical-Mechanical Planarization.**

Input Variables	Microscale Parameters	Nanoscale Interactions	Output Parameters
Particle characteristics	Pad	Chemomechanical	Removal rate
Size	Contact area	Dynamics of surface-layer formation	Planarization
Size distribution	Pressure on the pad	Thickness	Surface finish
Shape		Uniformity	Selectivity
Mechanical properties	Particles on the pad	Rate of formation	
Chemistry	Pressure	Layer removal mechanism	
Dispersion	Coverage	Abrasion frequency	
Concentration			
Agglomeration	Chemical concentration and distribution		
Oversized particles			
Slurry chemistry	Contact mode	Chemical and mechanical	
Oxidizers	Direct	Etching	
pH stabilizers	Mixed	Mechanical removal	
Complexing agents	Hydroplaning		
Dispersants			
Concentration			
pH and pH drift			
Down pressure and linear velocity			
Pad characteristics			
Mechanical properties			
Topography			
Conditioning			
Substrate characteristics			
Feature size			
Feature density			


and relative velocity of the particles across the wafer.<sup>7-9</sup> This equation was first suggested nearly 75 years ago for determining material removal when two plates were rubbed against each other. Subsequently, it was modified to incorporate particle-based polishing. Although this equation (with minor modifications) has been used extensively in CMP because of its apparent simplicity, it has two fundamental flaws that limit its applicability. First, this equation was developed for mechanical polishing only, without taking into account any chemical synergistic effects. Second, being a phenomenological equation, it fails to provide any insight into the interaction process, even from the mechanical viewpoint (e.g., the effects of particle size, concentration, and other slurry and pad variables). Based on these two reasons, Preston's law should not be the starting point for understanding CMP phenomena. Instead, new fundamental mechanistic approaches, which take into account synergistic mechanical and chemical effects,

and nonlinearities due to pad interactions, should be developed. The article by Singh et al. provides one such approach to address this issue.


A more elegant method for understanding the effect of the process variables is to determine the microscale and nanoscale effects that occur in CMP (Table 1). For example, if one decreases the particle size in a CMP slurry, the following micro-/nanoscale effects may occur: surface coverage of the particles on the pad may increase (microscale), material removal per particle may decrease due to lower stresses (nanoscale), and the degree of surface scratching may decrease due to reduced indentation (nanoscale). Similarly, if the chemicals are varied, the dynamics of layer formation can be altered. *In situ* measurements of these effects will represent an important step in understanding the mechanisms of the CMP process. In their article, Mounpour et al. describe some advanced analytical methods for characterizing CMP consumables and testing their interactions



**Figure 3** Schematic diagram showing the difference between CMP and chemical etching in their surface reaction kinetics. In chemical etching, the removal rate is constant and does not change with time. In the CMP process, the reactions between the chemicals and the metallic layers result in a thin, nondissolving, chemically passivating surface film, which is subsequently removed by the mechanical action of the particles. Initially, the chemical reaction rate is high, but due to passivation effects, the reaction rate drops immediately. When the surface layer is removed by the abrasive particles in the slurry, the surface film formation and passivation phenomenon repeats itself.



**Figure 4** Transient electrochemical current measurements as a function of time for a tungsten surface abraded in an oscillating motion with an alumina ball.



**Figure 5** Schematic diagram showing the removal rate and surface finish obtained using chemical etching, mechanical polishing, and CMP.

## Advances in Chemical-Mechanical Planarization

### CMP Advancements and Emerging Issues

With the introduction of CMP into the mainstream semiconductor industry less than 10 years ago, several advancements in tools, the process itself, and the consumables used (particularly slurries) have taken place to meet the increasing demands of the field. Compared with single-platen tools introduced initially, the new CMP tools have several platens and employ the dry-in and dry-out concept (in which the wafer enters and exits the process in a dry state) that integrates both the polishing and the cleaning processes with the same equipment.<sup>14</sup> Nonrotating platforms that enable elliptical and linear motion have been developed.<sup>14</sup> The tools are also equipped with state-of-the-art slurry handling systems, slurry mixing systems, and sophisticated multizone end-point detection controllers.

Significant changes have occurred in consumables, especially in the area of slurry formulation. Slurries containing smaller-sized nanoparticles and novel particles such as ceria have entered mainstream CMP applications.<sup>15</sup> Other functional particles, such as coated and nanoporous particles, have been demonstrated for CMP.<sup>16</sup> The development of "abrasive-free" slurries for soft materials such as copper has been an exciting new advance.<sup>17</sup> In the abrasive-free approach, chemicals are used to soften the oxide layer on copper so that it can be removed by the mechanical action of the pad. The elimination of particles in the slurry reduces the risk of surface defectivity during the polishing process. The article by Hanazono et al. highlights this approach.

Other promising abrasive-free approaches to copper polishing have been developed.<sup>16,19</sup> One such approach uses a "single-component" slurry to directly make a soft layer on the copper surface, which can then be mechanically removed by the polymer pad. An example of a blanket copper surface (copper deposited on an unpatterned wafer surface) before and after polishing using this method is shown in Figure 6.<sup>19</sup> The figure shows that the as-deposited copper surface has a rms roughness exceeding 65 nm, which can be reduced to less than 2 nm after short polishing times (30–45 s). Additionally, scanning electron microscopy of the polished surface shows the scratch-free polishing capability of this approach. Abrasive-free CMP slurries have the potential to considerably simplify slurry handling and monitoring, reduce surface defectivity and stresses, and significantly increase polishing selectivity with respect to the underlying tantalum or dielectric layer.

Other advancements in slurry engineering include the use of additives and chemi-




Figure 6 (a), (b) Scanning electron microscopy images and (c), (d) atomic force microscopy images of copper surfaces before (left) and after (right) the single-component abrasive-free CMP process

cals to further control CMP performance. One example is the development of low-stress slurries for CMP of copper interconnects on low- $\kappa$  substrates. The issues involved in polishing fragile low- $\kappa$  materials are highlighted in the article by Bajaj et al. The mechanical fragility of low- $\kappa$  dielectrics requires the use of slurries that produce low stresses on the surfaces. The softness of low- $\kappa$  materials, as compared with silica, makes them susceptible to scratching, delamination, and indentation when standard abrasives are used. By manipulating the particles as well as the additives, shear stress from the slurries can be significantly reduced. Figure 7 shows friction force measurements during polishing of a copper/low- $\kappa$  dielectric (carbon-doped silica) surface using standard silica abrasives and formulated slurries with specific additives.<sup>19</sup> The figure shows that shear forces can be significantly decreased by the use of specific additives in the slurry. One expects this type of approach to be further emphasized with the introduction of low- $\kappa$  materials in semiconductor production in the coming decade.

Another important area that is expected to show significant advancement is high-




Figure 7. Friction force measurements for conventional and low-stress CMP slurries used to polish a copper/low- $\kappa$  dielectric surface

planarity polishing of dielectric materials. Due to widely varying topographies of the surface, slurries have to be designed that will enhance the planarity of the polishing process. The polish rate of typical particle-based slurries increases linearly with applied pressure. Although this leads to planarization of the surface, slurries that have an even higher planarization capability are required, due to varying

## Advances in Chemical-Mechanical Planarization

pattern densities and periodicities. One method developed by 3M is the use of a pad embedded with abrasive silica/cerium-based particles.<sup>20</sup> These pads have been used to achieve high-planarity polishing of silica for shallow trench isolation (STI) applications. Slurries that exhibit non-Freestonian variations in polish rate as a function of pressure, resulting in high-planarity polishing, are expected to be used in the future for both dielectric and metal applications.<sup>19</sup>

The rapid miniaturization of semiconductor devices has placed more exacting requirements on the CMP process. Smaller devices require a high degree of control, and the manufacturing operation has a smaller process window. An example of these more stringent requirements is the STI process, which is used to isolate adjacent devices on a wafer. Issues such as nanotopography (nanometric changes across a millimeter length scale) may significantly lead to nonplanarity and limit our ability to achieve high-yield CMP processes. The article by Borung and Lee focuses on the effect of nanotopography in STI polishing.

### Emerging Applications

With the increased popularity of and familiarity with CMP technology to planarize surfaces and fabricate embedded submicron structures through polishing, new applications of this technology are expected to emerge at a rapid rate. The growth of microchip complexity based only on silicon technology is fast approaching fundamental limits.<sup>21</sup> New technologies that incorporate novel materials and structures onto silicon may become the driving force to significantly maintain or accelerate Moore's law (Gordon Moore's prediction that the computing power of a chip will double every 12-18 months). CMP is expected to play a key role in these next-generation micro- and nanofabrication technologies. Some of the potential areas in which CMP could play a significant role include the formation of gate electrodes for high- $\kappa$  dielectrics, gate structures and interconnect technology for ferroelectric and ferromagnetic nonvolatile memories, STI applications in high-speed Si-Ge devices, planarization of multidimensional microelectromechanical systems (MEMS), fabrication of three-dimensional memories and optical-bandgap materials, and planarization of III-V and other semiconductor substrates (aluminum nitride, gallium nitride, silicon carbide, diamond, etc.) for high-quality epitaxial growth. The article by Evans focuses on some future applications of CMP.

In all of these applications, CMP is considered an enabling technology, and its ap-

plications are expected to expand to more chemically complex materials and mechanically fragile structures. In this regard, there is immense room for integration of new fabrication technologies on silicon. An example of this is shown in the integration of embedded metal and oxide structures onto silicon by means of CMP.<sup>19</sup> Figure 8a shows a cathodoluminescent image of europium-doped yttrium oxide phosphor structures embedded in silica using CMP. These structures exhibit much brighter cathodoluminescence than a blanket flat film, thus showing great potential for field-emission display applications. Another example of the integration of novel magnetic structures onto silica is shown in Figure 8b. This figure shows embedded magnetic submicron cobalt structures distributed periodically inside a silica matrix. To make this structure, a conformal film of tantalum is deposited inside silica vias, followed by electrochemical deposition of cobalt and then planarization. Such structures are expected to be utilized in 3D patterned storage media or other device




Figure 8. Example of novel embedded structures obtained by CMP. (a) Europium-doped yttrium oxide phosphor structures embedded in silica using CMP. These structures exhibit much brighter cathodoluminescence than a blanket flat film, thus showing great potential for field-emission display applications. (b) Magnetic submicron cobalt structures embedded in a silica matrix. Such structures are expected to be used in three-dimensional patterned storage media or other device structures.

structures. It is expected that with further advancements in photolithography, even smaller nanoscale embedded structures will be fabricated in the future.

### References

1. A.E. Braun, *Semicond. Int.* 24 (November 2001) p. 51.
2. M.A. Corbett, *Solid State Technol.* 43 (December 2000) p. 72.
3. V. Shannon and D.C. Smith, *Semicond. Int.* 24 (May 2001) p. 93.
4. S. Wolf and R.N. Tauber, *Silicon Processing for the VLSI Era: Process Technology*, 2nd ed., Vol. 1 (Lattice Press, Sunset Beach, CA, 1999).
5. J.M. Steigerwald, S.P. Murarka, and R.J. Gutman, *Chemical-Mechanical Planarization of Microelectronic Materials* (John Wiley & Sons, New York, 1997).
6. S.M. Sze, *VLSI Technology*, 2nd ed. (McGraw-Hill, New York, 1988).
7. F. Preston, *J. Soc. Glass Technol.* 112 (1927) p. 14.
8. N.J. Brown, P.C. Baker, and R.T. Manley, in *Proc SPIE Contemporary Methods of Optical Fabrication*, Vol. 306 (SPIE—The International Society for Optical Engineering, Bellingham, WA, 1981) p. 42.
9. L.M. Cook, *J. Non-Cryst. Solids* 120 (1990) p. 152.
10. F.B. Kaufman, D.B. Thompson, R.E. Broadie, M.A. Jaso, W.L. Guthrie, D.J. Pearson, and M.B. Small, *J. Electrochem. Soc.* 138 (11) (1991) p. 3460.
11. S.-M. Lee, W. Choi, V. Craciun, S.-H. Jung, and R.K. Singh, "Electrochemical Measurements to Understand the Dynamics of the Chemically Modified Surface Layer Formation During Copper CMP," presented at Symposium I, Materials Research Society Meeting, San Francisco, April 2002, Paper No. 14.11.
12. U. Mahajan, M. Biemann, and R. K. Singh, *Electrochem. Solid-State Lett.* 2 (1999) p. 80.
13. M. Biemann, U. Mahajan, R.K. Singh, P. Agarwal, S. Mischler, E. Rosset, and D. Landolt, *Chemical-Mechanical Polishing: Fundamentals and Challenges*, edited by S.V. Babu, S. Danyluk, M. Krishnan, and M. Tsujimura (Mater. Res. Soc. Symp. Proc. 566, Warrendale, PA, 2000) p. 97.
14. For CMP tools, see Applied Materials Inc. Home Page, <http://www.amat.com>, the EBARA Technologies Inc. Home Page, <http://www.ebaratech.com>, and the Lam Research Home Page, <http://www.lamresearch.com> (accessed July 2002).
15. R.K. Singh, R. Bajaj, M. Mounpour, and M. Meuris, eds., *Chemical-Mechanical Polishing 2000: Fundamentals and Materials Issues* (Mater. Res. Soc. Symp. Proc. 623, Warrendale, PA, 2001).
16. R. Vacassy, R.J. Flatt, H. Hofmann, K.S. Choo, and R.K. Singh, *J. Colloid Interface Sci.* 227 (2000) p. 302.
17. S. Kondo, N. Sekuma, Y. Homma, Y. Goto, N. Ohashi, H. Yamaguchi, and N. Owada, *J. Electrochem. Soc.* 147 (2000) p. 3907.
18. J. Kelleher, C. Burkhardt, A. Batchelor, L. Guo, C.B. Little, and Y. Li, 7th International Chemical-Mechanical Planarization for ULSI Multilayer Interconnection Conference (CMP-MIC Proc. 02 IMIC-700P, 2002) p. 188.
19. R.K. Singh and S.-M. Lee (unpublished).
20. T.H. Lee, *Sci. Am.* 52 (January 2002) p. 286.



## Advances in Chemical-Mechanical Planarization

**Rajiv K. Singh**, Guest Editor for this issue of *MRS Bulletin*, is a professor in the Department of Materials Science and Engineering at the University of Florida. His research interests include the innovative synthesis, processing, and micro- and nanofabrication of materials and structures. In the last decade, he has worked in several semiconductor processing areas, including transient thermal processing of materials, chemical-mechanical planarization, diamond science and technology, and oxide-based electronics. Other areas of interest include the synthesis and processing of nanoparticles and nanoscale coatings on particles.

Singh obtained his BE degree in chemical engineering from Jadavpur University, India, in 1985, then earned his MS degree in materials science and engineering from North Carolina State University (1987) and a PhD degree from NCSU in 1989. He joined the University of Florida faculty in 1990 as an assistant professor and was promoted to associate professor in 1995 and full professor in 1997.

Singh has published more than 360 papers, and his group has presented over 400 conference presentations. His work has received over 2400 research citations. He has organized more than 20 international conferences and edited eight books, and he has been a guest editor for eight journal issues. Singh has given more than 130 invited talks and lectures at international conferences and institutions.

Singh has been awarded, or nominated for,

more than 16 U.S. and international patents in various areas of materials technologies, including diamond films, flat-panel displays, metal-ceramic joining and adhesion of hard materials, drug delivery systems, semiconductor processing (cleaning, planarization, and thin-film transistors), battery materials, and medical devices. He is the author of the SLIM (Simulation of Laser Interaction with Materials) software, which is used worldwide to model laser-solid interactions with materials. His research has resulted in the spinoff of two start-up companies, Nanotherapeutics Inc., which specializes in controlled drug delivery applications, and Sunmat Inc., which specializes in advanced materials products such as shingles for CMP. He played a key role in the establishment of the NSF-funded Engineering Research Center for Particle Science and Technology, where he directs CMP research efforts.

Singh is a fellow of ASM and the recipient of several awards, including the NSF Young Investigator Award, the Hardy Gold Medal from TMS, the IBM Faculty Development Award, the University of Florida Research Foundation Professor Award, and the MRS Graduate Student Award. He has held several visiting appointments, at the National University of Singapore, the National Institute of Materials and Chemical Research (Japan), and the Swiss Federal Institute of Technology.

Singh can be reached by e-mail at [rsing@mse.ufl.edu](mailto:rsing@mse.ufl.edu).



**Rajiv K. Singh**

**Rajeev Bajaj**, Guest Editor for this issue of *MRS Bulletin*, is director of technology at Applied Materials in Santa Clara, Calif. His experience includes product and technology development in chemical-mechanical planarization and electroplating technology. Prior to joining Applied Materials, he was the CMP development manager at Lam Research. He has held engineering positions at Motorola, the Advanced Products Research and Development Laboratory (APRDL), and Sematech. Bajaj earned his PhD degree in chemical engineering from the University of Texas at Austin in 1995 and his BS degree from Banaras Hindu University, India, in 1987. He holds 12 patents in applications and equipment design for CMP. He co-edited the proceedings volume *Chemical-Mechanical Polishing 2000—Fundamentals and Materials Issues* for MRS and has published and presented several articles on the subject of CMP.

He is a member of MRS and an industry-sponsoring member of the Engineering Research Center for Particle Science and Technology at the University of Florida.

Bajaj can be reached by e-mail at [Rajeev\\_Bajaj@amat.com](mailto:Rajeev_Bajaj@amat.com).



**Rajeev Bajaj**



**Zhan Chen**

**Jin Amanokura** is a researcher for the chemical-mechanical planarization materials project in the Semiconductor Materials Development Division of Hitachi Chemical Co. Ltd. in Tokyo. His interests include the development of polymer materials (photoresists, polymer electrolytes) through an electrochemical approach. He joined Hitachi in 1991 and received his BS degree in polymer science from the Tokyo University of Agriculture and Technology in 1992.

Amanokura can be reached by e-mail at [j-amanokura@hitachi-chem.co.jp](mailto:j-amanokura@hitachi-chem.co.jp).

**C. Bahar Basim** received her PhD degree in materials science and engineering from the University of Florida in 2002 with specialties in electronic materials and particle science and technology. Her dissertation research focused



**Jin Amanokura**



**Kyu-Se Choi**

on the design of engineered particulate systems for chemical-mechanical planarization applications. As a part of the CMP research group at the Engineering Research Center for Particle Science and Technology at the University of Florida, she has studied the impact of slurry-particle size distribution and stability and solids concentration on pad-particle-substrate interactions during CMP. She obtained her MSc degree in mining and minerals engineering from the Virginia Polytechnic Institute and State University in 1997, and her BSc degree in mining engineering from the Middle East Technical University in Ankara, Turkey.

Basim can be reached by e-mail at [gbasim@mse.ufl.edu](mailto:gbasim@mse.ufl.edu).

**Duane Boning** is an associate professor of electrical engineering and



## Advances in Chemical-Mechanical Planarization



G. Bahar Basim



Duane Boning



Ken Cadien



Wonseop Choi



David Evans

computer science at the Massachusetts Institute of Technology, as well as associate director of MIT's Microsystems Technology Laboratories. His research focuses on variation modeling, interconnect technology, and control in semiconductor processes, with special emphasis on chemical-mechanical polishing and plasma etching.

He earned his degrees from MIT in electrical engineering and computer science, including a PhD degree in 1991. From 1991 to 1993, he was a member of the technical staff at Texas Instruments in Dallas, where he worked on process and device simulation, tool integration, semiconductor process representation, and statistical modeling and optimization. Boning has more than 120 papers and conference presentations in these areas of research. He is editor in chief of *IEEE Trans-*

*actions on Semiconductor Manufacturing* and is a member of IEEE, ECS, MRS, and ACM.

Boning can be reached by e-mail at [boning@mitl.mit.edu](mailto:boning@mitl.mit.edu)

Ken Cadien is director of innovative technology and an Intel Fellow in the Technology and Manufacturing Group at Intel Corp. In his current position, he directs pathfinding activities related to advanced interconnects, focusing on chemical-mechanical planarization and metal deposition. He joined Intel in 1990 as a group leader for thin films, and in 1997, he was promoted to principal engineer, responsible for groups working in copper technology and advanced polishing. He was appointed Intel Fellow in 1999.

Cadien received his BA and ME degrees in metallurgy from McGill University in Montreal in 1974 and 1977, re-

spectively. In 1981, he received his PhD in materials science from the University of Illinois at Urbana-Champaign.

Prior to his work at Intel, he held thin-film engineering and research positions at Eastman Kodak and Westam Corp. He also was an assistant professor at Rensselaer Polytechnic Institute, Department of Materials Science and the Center for Integrated Electronics, from 1983 to 1986.

Cadien's work has been published in numerous journals, and he holds eight patents.

Cadien can be reached by e-mail at [kenneth.cadien@intel.com](mailto:kenneth.cadien@intel.com)

Zhan Chen is a senior engineer working at the Intel Corp. He currently conducts research and development on semiconductor device processing, including dielectric film deposition.

Chen received a BS degree in chemistry from Peking University in 1996 and a PhD degree in materials science and engineering from the University of Florida in 2000. As a graduate student, he worked in several areas, including chemical-mechanical planarization, front-end gate cleaning, micro-batteries, and phosphor and oxide thin films. He has also developed

several models that illustrate the interparticle forces during cleaning and CMP. His work has led to the development of novel, abrasive-free chemistries for copper polishing. He has co-authored 11 technical papers and has filed for two U.S. patents.

Chen can be reached by e-mail at [zhan.d2.chen@intel.com](mailto:zhan.d2.chen@intel.com).

Kyu-Se Choi is a PhD student in the Department of Materials Science and Engineering at the University of Florida. His current research involves the synthesis of nanoporous particles and coated particles for various advanced materials applications. His work has led to five publications and one pending U.S. patent. He received his BA degree from Chungnam National University in Taejeon, Korea.

Choi can be reached by e-mail at [kchoi@mse.ufl.edu](mailto:kchoi@mse.ufl.edu)

Wonseop Choi is a PhD student in the Department of Materials Science and Engineering at the University of Florida. His current studies focus on the verification of chemical-mechanical planarization mechanisms using *in situ* friction force measurements. He received his MS degree in metallurgical engineering from Hanyang University in Seoul, Korea, in 1998.

Choi can be reached by e-mail at [wchoi@mse.ufl.edu](mailto:wchoi@mse.ufl.edu)

David Evans is senior manager of the Integrated-Circuit Process Technology Laboratory at Sharp Laboratories of America Inc. in Camas, Wash. He is also

an adjunct professor in the Electrical and Computer Engineering Department within the Oregon Graduate Institute School of Science and Engineering at the Oregon Health and Science University, where he teaches IC process technology.

He received a BS degree in chemistry in 1974 from the University of Missouri at Rolla and a PhD degree from Iowa State University in 1980. He worked in semiconductor processing and flat-panel display R&D and manufacturing for Tektronix Inc. of Beaverton, Oregon, from 1980 to 1994. During this time, his interests involved plasma processing, liquid-crystal displays, and thin-film deposition. In 1994, he joined the IC Process Technology Lab, which was then a research arm of Sharp Microelectronics Technology; this group subsequently became part of Sharp Laboratories. While at Sharp, he has worked on various semiconductor processes and materials, with particular emphasis on CMP of new materials and device structures.

Evans can be reached by e-mail at [DEvans@sharp-labs.com](mailto:DEvans@sharp-labs.com).

Masanobu Hanazono has been a general manager of the chemical-mechanical planarization project in the Semiconductor Materials Development Division of Hitachi Chemical Co. Ltd. in Tokyo since 1998. His research interests include the development and investigation of novel materials for thin-film devices and semiconductors.

Hanazono received his MS degree in applied chemistry from the

## Advances in Chemical-Mechanical Planarization

University of Hokkaido in 1967 and then joined the Hitachi Research Laboratory, where his research mainly focused on the development and evaluation of thin-film devices for magnetic recording, liquid-crystal displays, and semiconductors. He also was manager of the thin-film device development group in the same laboratory. He received his PhD degree from the University of Hokkaido in 1982.

In 1992, he transferred to Hitachi Chemical as a manager of the planning section, where he oversaw research on new-wave approaches for new devices. As a project leader since 1998, he has concentrated on the development of CMP slurries. In 2001, he received an R&D 100 Award for the development of an abrasive-free slurry for CMP of copper.

Hanazono can be reached by e-mail at [m-hanazono@hitachi-chem.co.jp](mailto:m-hanazono@hitachi-chem.co.jp).

Yasuo Kamigata has been a staff researcher with the chemical-mechanical planarization materials project in the Semiconductor Materials Development Division of Hitachi Chemical Co. Ltd. in Tokyo since 1998. His research interests include the development of functional devices and materials that make use of inorganic substances. He received his MS degree in applied chemistry from Tokyo Metropolitan University in 1985 and joined Hitachi Chemical soon afterward.

Kamigata can be reached by e-mail at [y-kamigata@hitachi-chem.co.jp](mailto:y-kamigata@hitachi-chem.co.jp).

Brian Lee received a BE degree from The Cooper Union in New York City in 1996, and SM and PhD degrees from the Massachusetts Institute of Technology in 1998 and 2002, respectively, both in electrical engineering. His principal research interests involve modeling and characterization of shallow trench isolation and chemical-mechanical planarization processes. Lee is a member of the Materials Research Society, Tau Beta Pi, and Eta Kappa Nu.

Lee can be reached by e-mail at [lee21@mit.edu](mailto:lee21@mit.edu).


Seung-Mahn Lee is a PhD student in the Department of Materials Science and Engineering at the University of Florida. His current research focuses on the study of chemical-mechanical planarization mechanisms, including *in situ* electrochemistry and the kinetics of surface-layer formation during CMP of metal films. His work has led to the development of novel slurries for the polishing of copper and refractory layers. He is the author of 10 papers and has filed two U.S. patents. He earned BSc and MSc degrees in metallurgical engineering from Korea University in 1994.

Lee can be reached by e-mail at [slee@mse.ufl.edu](mailto:slee@mse.ufl.edu).

Mansour Moinpour is the materials technology and engineering manager at Intel Corp., where he focuses on materials development, selection, and characterization for chemical-mechanical planarization and advanced dielectric materials for Intel's integrated-circuit fab-



Masanobu Hanazono



Andrea Ochler

rication technologies. Previously, he was responsible for CMP equipment selection and improvements. From 1994 to 1997, he worked with Intel's California Technology and Manufacturing Group, where he was responsible for process and technology development in CMP, chemical vapor deposition, and metallization areas for advanced deep-submicron logic and flash memory devices.

Moinpour received his PhD degree in materials science and engineering from the University of Washington, Seattle, in 1987. Before joining Intel in 1991, he served as a research assistant professor and lecturer in the Departments of Electrical Engineering and Materials Science and Engineering at the University of Washington. He has served on the industry faculty advisory committee of the department since 1995. He is also an



Yasuo Kamigata



Tony Pan

affiliated advisory committee member for the Department of Mechanical Engineering at Tufts University. Moinpour is the past chair of the planning committee of the CMP Users Group of the Northern California Chapter of AVS. He has authored or co-authored more than 90 technical publications and holds eight patents.

Moinpour can be reached by e-mail at [mansour.moinpour@intel.com](mailto:mansour.moinpour@intel.com).

Brj M. Moudgil is a professor of materials science and engineering at the University of Florida and director of the NSF's Engineering Research Center for Particle Science and Technology there. Moudgil's research interests include selective surfactant and polymer coatings for targeted applications in advanced materials and minerals processing, microelectronics manu-



Seung-Mahn Lee



Rahul Surana

facture, and pharmaceutical formulations. His group has performed pioneering research by measuring and modeling the effect of nanoscale roughness and humidity on interparticle forces. These studies have provided new insights into aggregation and dry dispersion phenomena critical to process and product design and development. His current research in understanding the role of self-assembled surfactant structures in dispersing nanoparticles and in modulating the friction forces on nano-rough surfaces, as encountered in the CMP process, is expected to be of major significance in developing design protocols for next-generation CMP slurries.

Moudgil's research accomplishments have been recognized by several awards, including his recent election to the National Academy of

## Advances in Chemical-Mechanical Planarization



Mansour Moinspour



Brij M. Moudgil



Mehul Naik



Alex Tregub



Ajoy Zutshi

Engineering (2002), the Antoine M. Gaudin Award from SME (1996), the Robert H. Richards Award from ADME (1995), and the Frank F. Aplan Award from the United Engineering Foundation (1997). He has published more than 180 technical papers, edited or co-edited nine books, and has presented more than 360 papers at scientific meetings and seminars at academic institutions and private organizations, both in the U.S. and abroad. He has been awarded 14 patents.

Moudgil can be reached by e-mail at [bmoudgil@ert.uci.edu](mailto:bmoudgil@ert.uci.edu).

Mehul Naik is a senior member of technical staff in the Process Modules Group at Applied Materials in Santa Clara,

Calif. He has worked on a variety of projects, including the first Endura system to have CVD and PVD chambers on the same mainframe to integrate CVD Al, CVD TiSiN, and PVD AlCu. He has worked on Al/low- $\kappa$  integration and was the lead engineer on the Cu/low- $\kappa$  integration effort as part of the overall process-module development at Applied Materials.

Naik can be reached by e-mail at [Mehul\\_Naik@amat.com](mailto:Mehul_Naik@amat.com).

Andrea Oehler joined Intel Corp. in 1995 and is currently a staff engineer focusing on the development, characterization, and manufacturability of new chemical-mechanical planarization slurries for process optimization

and new process modules. She is a mentor for Clarkson University's Semiconductor Research Corp. (SRC) program, working with abrasives in CMP. She received BA and PhD degrees in materials science from Rensselaer Polytechnic Institute in 1988 and 1995, respectively, where she studied the chemical reactions of silica with water.

Oehler can be reached by e-mail at [andrea.oehler@intel.com](mailto:andrea.oehler@intel.com).

Tony Pan is an engineering manager in the Process Module Group at Applied Materials in Santa Clara, Calif. His areas of study have involved process development in integrated-circuit fabrication and microelectronics, including thin-film, etching, planarization, and process integration. Before joining Applied Materials, he worked in process development and research at Xerox Integrated Circuit Lab, MCC Corp., and Tandem Computers. He earned a BS degree in physics from the National Taiwan University as well as MS and PhD degrees in materials science and engi-

neering from Cornell University.

Pan can be reached by e-mail at [Tony\\_Pan@amat.com](mailto:Tony_Pan@amat.com).

Rahul Surana is a process engineer with the Process Module Group at Applied Materials in Santa Clara, Calif. His research has focused on copper chemical-mechanical planarization (CMP), and more recently, he has worked to solve copper wiring issues related to CMP, electroplating, and barrier seed. He earned a PhD degree in chemical engineering from the Pennsylvania State University.

Surana can be reached by e-mail at [Rahul\\_Surana@amat.com](mailto:Rahul_Surana@amat.com).

Alex Tregub has been a staff engineer at Intel Corp. since 2000. His responsibilities include the characterization of materials for chemical-mechanical planarization and low- $\kappa$  and lithography processes. His expertise mainly involves mechanical, structural, thermoanalytical, and adhesion analysis and the manufacturing technology for polymers and polymer composites.

Tregub holds an MS degree in electronics from Kiev Polytechnic Institute and a PhD degree in chemistry from the Institute of Macromolecules at the Ukrainian Academy of Science. He has authored or co-authored more than 60 scientific and technical publications, including patents and invited reviews. Before joining Intel, he served

as a senior staff engineer at Kaiser Aerospace Co. He has held research positions at the University of California, San Diego; the Hebrew University of Jerusalem; the Institute of Macromolecules, Kiev; and the Institute for Nuclear Physics, Kiev. From 1993 to 1994, he was the recipient of the international Alexander von Humboldt scholarship and was a Humboldt Foundation fellow at the University of Ulm, Germany. He is a member of SAMPE, the New York Academy of Sciences, NATAS, ACS, and IEEE, and serves as the vice president of the Los Angeles SAMPE chapter and chair of the Bay Area Thernal Analytical Society (BATAS). He is also a member of the ISMT advisory board (soft pellicles).

Tregub can be reached by e-mail at [alexander.tregub@intel.com](mailto:alexander.tregub@intel.com).

Ajoy Zutshi has been a senior engineering manager at Applied Materials in Santa Clara, Calif., since 1999. His current research involves copper process integration. He received his PhD degree in ceramic science and engineering from Rutgers University in 1992. Since 1996, he has held several positions in the semiconductor equipment industry. Zutshi has several patents and has published more than 50 works.

Zutshi can be reached by e-mail at [Ajoy\\_Zutshi@amat.com](mailto:Ajoy_Zutshi@amat.com). □

Materials Research Society online catalog for Proceedings & Exhibitions  
[www.mrs.org/publications/](http://www.mrs.org/publications/)

This Page is inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

## BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLORED OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REPERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images problems checked, please do not report the problems to the IFW Image Problem Mailbox**